


REFINISH
**Technical Data Sheet
TDS**

Description

UHS CLEAR is a 2K ultra high solid clearcoat with very low solvent content especially formulated to comply with the most restrictive legislation concerning solvent emissions.

UHS CLEAR can be used for spot-repair, full panel, or total respray, in 2-3 stage finishes, for best results and durability.

UHS CLEAR offers high solid content, fast drying strong film hardness, and excellent gloss, with the flexibility of different hardener options, for different types of repair.

Technical details form supplied product

	UHS Clear	UHS Hardener
Viscosity, DIN4 20°C	47" ± 2	26" ± 2
Solids Content %	54 ± 1	75 ± 1
Density 20°C	1,00 ± 0,03	1,08 ± 0.03
VOC content grams/litre	< 460	< 250
Gloss	<95	-----
Pack Size	1L	0,33L

Preparation

	By volume	By weight	Percentage
S 830 Clearcoat	1000ml	1000g	100%
Hardener: S 431 / S 432 / S 433 ("BS REFINISH" UHS HARDENER)	330ml	356g	33%
Thinner : S 709 / S 710 / S 711 ("BS REFINISH" ACRYL. THINNER)	266 – 399ml	240 – 360g	20-30%
Ready for use viscosity DIN4 20°C	15-18" ± 2		
Ready for use solids content %	59 ± 1		
Pot Life	2 hours @ 20°C		

Application

	Conventional	High transfer efficienc
Gravity spray gun		
Gun nozzle	1,3-1,4	1,2-1,3
Pistol pressure	3-3,5 bar	2 bar
Suction feed spray gun		
Gun nozzle	1,4-1,6	1,2-1,3
Pistol pressure	3-3,5 bar	2 bar
Flash between coats	15-20 minutes @ 20°C	
Number of coats	1 medium coat and 1 full coat or 2 full coats	
Suggested thicknes	50microns	

Drying

	20°C	50-60°C
Temperature		
Dust free	15 minutes	Flash before force dry 15 minutes
Handling	24 hours	30-40 minutes
Ready to be polished after	24 hours	12 hours

	Medium wave	Short wave
INFRARED DRYIN		
Flash before infrared drying @ 20°C	5-7 minutes	5-7 minutes
Ready to be polished after	25 minutes	20 minutes


REFINISH
**Technical Data Sheet
TDS**

Hardeners - Thinners
Hardeners

S 431 Slow	To be used from 25 °C to 35 °C
S 432 Normal	To be used from 15 °C to 25 °C
S 433 Fast	To be used from 5 °C to 15 °C (Spot repairs @ 25 °C)

Thinners

S 709 Slow	To be used from 25 °C to 35 °C
S 710 Normal	To be used from 15 °C to 25 °C
S 711 Fast	To be used from 5 °C to 15 °C (Spot repairs @ 25 °C)

Additional information

Dry sanding P 800-1000

Wet sanding P 1200-2500

Clean

Follow all safety requirements
These products are for professional use only

and are not to be used for purposes other than those specified.

The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps in order to ensure the suitability of the product for the intended purpose.

For further information please contact.
Manufacturer

SERANO Company
6, Skra str. 55236, Panorama
Thessaloniki - Greece
e-mail: info@bsrefinish.com
fax: +30 2310 341988
<http://www.bsrefinish.com>

Distributor


"BS Refinish" and BS Refinish logo are trademarks of SERANO Company.
Copyright © 2011 SERANO Company. All rights reserved.